








## MORILITE

Formulation	Color	 HARDNESS	 DENSITY	 ABRASION RESISTANCE	ELONGACION & TRACTION		 TEAR STRENGTH	 FLEX RESISTANCE	Thermoformable	REACH Attachment XVII	CADS Compliant RSL 2021
		DIN 53 505	DIN 53 479	DIN 53 516 EN 12770	Tensile Strength	Extension at Break	ISO 20872	BS 5 131: 1.1.2			
		ShA	g/cm <sup>3</sup>	mm <sup>3</sup>	MPa	%	N/mm	mm/kcycle			
S394.02	Black	94±2	1.32±0.02	≤ 400	≥ 7	≥ 200	≥ 7	≤ 0.10		✓	
S394.95	Ochre 95	94±2	1.33±0.02	≤ 350	≥ 7	≥ 200	≥ 7	≤ 0.10		✓	
S394.97	Ochre 97	94±2	1.30±0.02	≤ 350	≥ 7	≥ 200	≥ 7	≤ 0.10		✓	
S394.14	Brown 14	94±2	1.31±0.02	≤ 400	≥ 7	≥ 200	≥ 7	≤ 0.10		✓	
S390.95	Ochre 95	90±2	1.32±0.02	≤ 350	≥ 7	≥ 200	≥ 7	≤ 0.10		✓	
S382.02	Black	85±2	1.31±0.02	≤ 350	≥ 7	≥ 200	≥ 7	≤ 0.10		✓	
S382.95	Ochre 95	85±2	1.31±0.02	≤ 350	≥ 7	≥ 200	≥ 7	≤ 0.10		✓	
S134.02	Black	98±2	1.43±0.02	≤ 500	≥ 7	≥ 200	≥ 7		✓	✓	
S134.95	Ochre 95	98±2	1.47±0.02	≤ 500	≥ 7	≥ 200	≥ 7		✓	✓	
S134.97	Ochre 97	98±2	1.45±0.02	≤ 500	≥ 7	≥ 200	≥ 7		✓	✓	
S394A.02	Black	94±2	1.31±0.02	≤ 400	≥ 7	≥ 200	≥ 7	≤ 0.10		✓	
S394B.02	Black	94±2	1.31±0.02	≤ 400	≥ 7	≥ 200	≥ 7	≤ 0.10		✓	✓
S394B.97	Ochre 97	94±2	1.31±0.02	≤ 400	≥ 7	≥ 200	≥ 7	≤ 0.10		✓	✓

Date: January 2021

**Monteiro, Ribas - Indústrias, SA**

Circunvalação, 9020 Apartado 52511 4202-351 Porto, Portugal

+351 228 338 673, www.monteirofootwear.com

NIF/VAT: PT 500 196 435, Capital social: 5.469.950,00, C.R.C. do Porto